



AMF THERMATEX® Feinstratos

- THERMATEX® Feinstratos creates an even, structured ceiling appearance through its finely ground surface
- Good sound attenuation (34 dB)
- Good light reflectance (85%)
- Ideal for retail, offices and meeting rooms, installations rooms or production areas



AMF THERMATEX® FEINSTRATOS

Edge details Additional edge details on request		Board 	Tegular 24 	Tegular 15 														
Thickness (mm)		15	15	15														
Dimensions (mm) Additional sizes on request		600 x 600 625 x 625 1200 x 600 1250 x 625	600 x 600 625 x 625 1200 x 600	600 x 600 1200 x 600														
System		Exposed demountable - System C Exposed - Bandraaster, demountable - System I.3 Exposed - Corridor, demountable - System F.3																
Weight		3.8 - 4.0 kg / m ²																
Colour		White																
Sound absorption		EN ISO 354 $\alpha_w = 0.20$ as per EN ISO 11654 - Class E <table border="1"> <thead> <tr> <th>Frequency f (Hz)</th> <th>125</th> <th>250</th> <th>500</th> <th>1000</th> <th>2000</th> <th>4000</th> </tr> </thead> <tbody> <tr> <td>α_p Board, Tegular</td> <td>0.35</td> <td>0.20</td> <td>0.15</td> <td>0.15</td> <td>0.20</td> <td>0.20</td> </tr> </tbody> </table> NRC = 0.15 as per ASTM C 423			Frequency f (Hz)	125	250	500	1000	2000	4000	α_p Board, Tegular	0.35	0.20	0.15	0.15	0.20	0.20
Frequency f (Hz)	125	250	500	1000	2000	4000												
α_p Board, Tegular	0.35	0.20	0.15	0.15	0.20	0.20												
Sound attenuation		EN ISO 10848-2 $D_{n,f,w} = 34$ dB as per EN ISO 717-1																
Sound reduction		EN ISO 10140-2 $R_w = 21$ dB as per EN ISO 717-1																
Fire reaction		Euroclass A2-s1, d0 as per EN 13501-1	RUS KM1 (G1, V1, D1, T1) as per FZ 123															
Light reflectance		85%																
Thermal conductivity		$\lambda = 0.060$ W/m K as per EN 12667																
Humidity resistance		95% RH																
Indoor air quality		 A+	 E1															
Cleanability																		
Sustainability		 EN ISO 14021 37-43%	 EN ISO 14025	 BIOSOLUBLE WOOL EC 1272/2008 Annex Q														

Products may vary from country to country.
Please contact your local sales representative.
For further information and legal notice, please visit our website.